

# Specifications

Product Name	Neodymium $\Phi$ 8mmx5mm				
Product Code	ND0017				
Content	Name	Symbol	SI		CGS
Shape	Diameter	D	8	mm	0.8 cm
	Height	H	5	mm	0.5 cm
	Dimensional tolerance +/-	D	0.1	mm	0.01 cm
		H	0.1	mm	0.01 cm
	Magnetization direction	M	Axial direction		
Surface treatment	NiCuNi	12	$\mu$ m	-	
Magnetic Properties	Surface flux density	B	417.1	mT	4171 G
	Attractive and Adsorptive Force	F	1.68	kgf	1684 gf
	Operating Point Flux Density	Bd	766	mT	7660 G
	Total Flux	$\phi_o$	0.0000385	Wb	3850 Mx
	Permeance Coefficient	Pc	1.88	Pc	-
	Operating Temperature Limit	Tw	90	$^{\circ}$ C	194 $^{\circ}$ F
Material Properties	Material Symbol	Neodymium	35		
	Residual Flux Density	Br	1170-1220	mT	11.7-12.2 kG
	Coercive Force	Hcb	$\geq$ 868	kA/m	$\geq$ 10.9 kOe
	Intrinsic coercive force	Hcj	$\geq$ 955	kA/m	$\geq$ 12 kOe
	Maximum energy product	BH	263-287	kJ/m <sup>3</sup>	33-36 MGOe
	Temperature coefficient	Br	-0.12	%/ $^{\circ}$ C	31.78 %/ $^{\circ}$ C
		Hcj	-0.55	%/ $^{\circ}$ C	31.01 %/ $^{\circ}$ C
	Heat resistance temperature	Tw	$\leq$ 80	$^{\circ}$ C	$\leq$ 176 $^{\circ}$ F
	Curie temperature	Tc	310	$^{\circ}$ C	590 $^{\circ}$ F
	Density	$\rho$	7.5	kg/m <sup>3</sup>	-
Weight	Net	0.00188	kg	1.88 g	
Remarks	REACH RoHS Directive				

All magnetic property values are for reference only. Please use them only as reference values when referring to actual magnetic application products or for research and development. We are not responsible for any liability resulting from the use of reference values. The contents of this document are subject to change without notice due to improvements or other reasons.