## **Specifications**

| Product Name        | Neodymium Φ10mmx25mm               |           |                 |            |           |      |
|---------------------|------------------------------------|-----------|-----------------|------------|-----------|------|
| Product Code        | ND0313                             |           |                 |            |           |      |
| Content             | Name                               | Symbol    | SI              |            | CGS       |      |
| Shape               | Diameter                           | D         | 10              | mm         | 1         | cm   |
|                     | Height                             | Н         | 25              | mm         | 2.5       | cm   |
|                     | Dimensional tolerance              | D         | 0.1             | mm         | 0.01      | cm   |
|                     | +/-                                | Н         | 0.1             | mm         | 0.01      | cm   |
|                     | Magnetization<br>direction         | М         | Axial direction |            |           |      |
|                     | Surface treatment                  | NiCuNi    | 12              | μm         | -         |      |
| Magnetic Properties | Surface flux density               | В         | 538.4           | mΤ         | 5384      | G    |
|                     | Attractive and<br>Adsorptive Force | F         | 4.14            | kgf        | 4149      | gf   |
|                     | Operating Point Flux<br>Density    | Bd        | 1100.6          | mT         | 11006     | G    |
|                     | Total Flux                         | φо        | 0.00008644      | Wb         | 8644      | Mx   |
|                     | Permeance Coefficient              | Pc        | 12.25           | Pc         | -         |      |
|                     | Operating<br>Temperature Limit     | Tw        | 150             | °C         | 302       | °F   |
| Material Properties | Material Symbol                    | Neodymium | 35              |            |           |      |
|                     | Residual Flux Density              | Br        | 1170-1220       | mT         | 11.7-12.2 | kG   |
|                     | Coercive Force                     | Hcb       | ≧868            | kA/m       | ≧10.9     | kOe  |
|                     | Intrinsic coercive force           | Hcj       | ≧955            | kA/m       | ≧12       | kOe  |
|                     | Maximum energy product             | ВН        | 263-287         | kJ/m3      | 33-36     | MGOe |
|                     | Temperature                        | Br        | -0.12           | %/°C       | 31.78     | %/°C |
|                     | coefficient                        | Hcj       | -0.55           | %/°C       | 31.01     | %/°C |
|                     | Heat resistance<br>temperature     | Tw        | ≦80             | °C         | ≦176      | °F   |
|                     | Curie temperature                  | Тс        | 310             | $^{\circ}$ | 590       | °F   |
|                     | Density                            | ρ         | 7.5             | kg/m3      | -         |      |
|                     | Weight                             | Net       | 0.0147          | kg         | 14.7      | g    |
| Remarks             | REACH RoHS Directive               |           |                 |            |           |      |

All magnetic property values are for reference only. Please use them only as reference values when referring to actual magnetic application products or for research and development. We are not responsible for any liability resulting from the use of reference values. The contents of this document are subject to change without notice due to improvements or other reasons.