

Specifications

Product Name					
Product Code	ND1191				
Content	Name	Symbol	SI		CGS
Shape	Diameter	D	1	mm	0.1 cm
	Height	H	0.8	mm	0.08 cm
	Dimensional tolerance +/-	D	0.1	mm	0.01 cm
		H	0.1	mm	0.01 cm
	Magnetization direction	M	Axial direction		
	Surface treatment	NiCuNi	12	μm	-
Magnetic Properties	Surface flux density	B	168.7	mT	1687 G
	Attractive and Adsorptive Force	F	0.031	kgf	31 gf
	Operating Point Flux Density	Bd	849.3	mT	8493 G
	Total Flux	φ o	0.00000066	Wb	66 Mx
	Permeance Coefficient	Pc	2.58	Pc	-
	Operating Temperature Limit	Tw	90	°C	194 °F
Material Properties	Material Symbol		35		
	Residual Flux Density	Br	1170-1220	mT	11.7-12.2 kG
	Coercive Force	Hcb	≥868	kA/m	≥10.9 kOe
	Intrinsic coercive force	Hcj	≥955	kA/m	≥12 kOe
	Maximum energy product	BH	263-287	kJ/m3	33-36 MGOe
	Temperature coefficient	Br	-0.12	%/°C	31.78 %/°C
		Hcj	-0.55	%/°C	31.01 %/°C
	Heat resistance temperature	Tw	≤80	°C	≤176 °F
	Curie temperature	Tc	310	°C	590 °F
	Density	ρ	7.5	kg/m3	-
	Weight	Net	0.0000047	kg	0.0047 g

All magnetic property values are for reference only. Please use them only as reference values when referring to actual magnetic application products or for research and development. We are not responsible for any liability resulting from the use of reference values. The contents of this document are subject to change without notice due to improvements or other reasons.